

**TECHNICAL INFORMATION**

<b>BRICK NAME</b>	<b>CATEGORY 38 COMPRISING OF:</b> Imperial Accrington Smooth Red – Dual Faced
<b>BRICK TYPE</b>	Through colour clay extruded brick
<b>SPECIFICATION</b>	Manufactured to EN 771-1:2011+A1 :2015
<b>SIZE*</b>	75 x 230 x 110mm 80 x 230 x 110mm
<b>DIMENSIONAL TOLERANCE</b>	T2
<b>RANGE</b>	R2
<b>COMPRESSIVE STRENGTH</b>	≥ 75 N/MM <sup>2</sup>
<b>WATER ABSORPTION</b>	≤ 6%
<b>SOLUBLE SALT CLASSIFICATION</b>	S2
<b>MOISTURE MOVEMENT</b>	≤ 0.20 MM/N
<b>BOND STRENGTH</b>	≤ 0.15 N/MM <sup>2</sup>
<b>NET DRY DENSITY</b>	1550 KG/M <sup>3</sup>
<b>PACKAGING</b>	Shrink wrapped on wooden pallets in packs of 384 (75mm, Imperial Accrington Smooth Red) 320 (80mm, Imperial Accrington Smooth Red)
<b>PACK SIZE; LxWxH</b>	1100 x 1100 x 1100mm Approx.
<b>PACK WEIGHT</b>	1.2 Tonnes Approx.
<b>USAGE</b>	Always mix from several packs, working vertically down the blades, not horizontally across the tops of the packs.
<b>SAMPLES</b>	Samples will be supplied on request.
<b>DURABILITY</b>	F2
<b>PERFORMANCE</b>	The recommendations of good practice made in the relevant British Standards regarding design and workmanship must be fully observed. Liability cannot be accepted for the performance of the product if used outside our recommendations. Guidance on the use of these bricks in specific situations is readily available from us.

\*Individual bricks may vary dimensionally; this is a natural characteristic of fired clay bricks and is catered for in the relevant European Standard.

