

**TECHNICAL INFORMATION**

<b>BRICK NAME</b>	<b>CATEGORY 9 COMPRISING OF:</b> Outside Blend Weathered Outside Blend Tumbled Weathered Outside Blend Pre War Common – Dual Faced Tumbled Weathered Pre War Common
<b>BRICK TYPE</b>	Through colour clay pressed brick
<b>SPECIFICATION</b>	Manufactured to BS EN 771-1
<b>SIZE*</b>	73 x 215 x 102.5mm 65 x 215 x 102.5mm
<b>DIMENSIONAL TOLERANCE:</b>	T2
<b>RANGE:</b>	R2
<b>COMPRESSIVE STRENGTH</b>	Mean - 44.8 N/MM <sup>2</sup>
<b>WATER ABSORPTION</b>	Mean - 22%
<b>SOLUBLE SALT CLASSIFICATION</b>	S2
<b>PACKAGING</b>	Shrink wrapped on wooden pallets in packs of 540 (Outside Blend, Weathered Outside Blend, Pre War Common- Dual Faced) 500 (Tumbled Weathered Outside Blend, Tumbled Weathered Pre War Common)
<b>PACK SIZE; LxWxH</b>	1100 x 1100 x 1100mm Approx.
<b>PACK WEIGHT</b>	1.3 / 1.7 Tonnes Approx.
<b>USAGE</b>	Always mix from several packs, working vertically down the blades, not horizontally across the tops of the packs.
<b>SAMPLES</b>	Samples will be supplied on request.
<b>DURABILITY</b>	F1
<b>PERFORMANCE</b>	The recommendations of good practice made in the relevant British Standards regarding design and workmanship must be fully observed. Liability cannot be accepted for the performance of the product if used outside our recommendations. Guidance on the use of these bricks in specific situations is readily available from us.

\*Individual bricks may vary dimensionally; this is a natural characteristic of fired clay bricks and is catered for in the relevant European Standard.

