



# ORIGINAL GISCOL COMMON



PRODUCT CODE	WCGISCOL/SOL/65 WCGISCOL/SOL/73
BRICK TYPE	Through colour clay extruded brick.
SPECIFICATION	Manufactured to BS EN 771-1
SIZE	65 x 215 x 102.5mm 73 x 215 x 102.5mm
DIMENSIONAL TOLERANCE	T1
RANGE	R1
COMPRESSIVE STRENGTH	Mean – 41.4 N/MM <sup>2</sup>
WATER ABSORPTION	Mean – 16%
SOLUBLE SALT CLASSIFICATION	S2
DURABILITY	F2
PACKAGING	Shrink wrapped on wooden pallets in packs of 550 (65 x 215mm) 500 (73 x 215mm)
PACK SIZE: L X W X H	1100 x 1100 x 1100mm Approx.
PACK WEIGHT	1.5 Tonnes Approx.
USAGE	Always mix from several packs, working vertically down the blades, not horizontally across the tops of the packs.
PERFORMANCE	The recommendations of good practice made in the relevant British Standards regarding design and workmanship must be fully observed. Liability cannot be accepted for the performance of the product if used outside our recommendations. Guidance on the use of these bricks in specific situations is readily available from us.
DOP COMMON ROOT REF CODE	CAT 47 – CPW – 2021



For more information on products, services, advice and technical guidelines please contact our Sales Team.

01746 330994  
[sales@imperialbricks.co.uk](mailto:sales@imperialbricks.co.uk)  
[www.imperialbricks.co.uk](http://www.imperialbricks.co.uk)

Individual bricks may vary dimensionally; this is a natural characteristic of fired clay bricks and is catered for in BS EN 771-1. Technical data correct at time of issue. Always order samples before purchasing and follow good site practice guidelines.



Sedex Member

VERISIO

LUCIDEON  
providing material solutions



UK  
 CA